

# **Tangra**<sup>™</sup> **M**

N-Type High efficiency Bifacial Single Glass Module

TS-BWT72(585-605)



Bifacial technology allows for the harvesting of up to an additional 30% energy from the rear side of the module.



30 years lifespan brings 10-30% additional power generation comparing with conventional P-type module.



N-type solar cell has no LID naturally which can increase power generation.



Excellent low irradiance performance.



Enhanced light trapping and optimized current collection contribute to the improvement of both module power output and reliability.



Industry leading lowest thermal coefficient of power.



Design optimized for lower operating current, resulting in minimized hot spot loss and improved temperature coefficient.



Certified to withstand: wind load (2400 Pa) and snow load (5400 Pa).



100% triple EL test enables remarkable reduction of module hidden crack rate.


## **RE INSURANCE**

Warranty partner






\* Optional performance warranty insurance. Please contact our local sales staff for more information.



# LINEAR PERFORMANCE WARRANTY



years

Product quality & process warranty

**30** years Linear power quarantee

**0.40**<sub>%</sub>
Annual degradation Over 30 years

# **COMPREHENSIVE CERTIFICATES**



ISO 9001: Quality Management System

ISO 14001: Environmental Management System Standard

ISO 45001: International Occupational Health and Safety Assessment System Standard

\* Different markets have different certification requirements. Also, the products are under rapid innovation. Please confirm the certification status with regional sales representatives.



Model of modules	TS-BWT	TS-BWT72(585) TS-BWT72(590)		TS-BWT72(595)		TS-BWT72(600)		TS-BWT72(605)		
	STC	NMOT	STC	NMOT	STC	NMOT	STC	NMOT	STC	NMOT
Peak power - $P_{mp}(W)$	585	436	590	440	595	443	600	447	605	451
Open circuit voltage - V <sub>oc</sub> (V)	52.09	49.17	52.25	49.35	52.47	49.53	52.66	49.71	52.85	49.89
Short circuit current - $I_{sc}(A)$	13.68	11.05	13.75	11.10	13.82	11.15	13.89	11.20	13.96	11.25
MPP voltage - V <sub>mp</sub> (V)	44.61	41.76	44.74	41.88	44.85	42.00	44.97	42.12	45.08	42.24
MPP current - $I_{mp}$ (A)	13.12	10.44	13.19	10.50	13.27	10.56	13.35	10.62	13.43	10.68
Module efficiency - $\eta_m$ (%)	22	2.6	22	2.8	23	3.0	23	3.2	23	3.4

STC (Standard Testing Conditions): Irradiance 1000W/m², Cell Temperature 25 °C , Spectra at AM1.5

NMOT (Nominal Module Operating Temperature): Irradiance 800W/m², Ambient Temperature 20℃, Spectra at AM1.5, Wind at 1m/s

## ELECTRICAL CHARACTERISTICS WITH DIFFERENT POWER BIN (REFERENCE TO 13.5% IRRADIANCE RATIO)

Peak power - P <sub>mp</sub> (W)	648	654	659	665	671
Open circuit voltage - V <sub>oc</sub> (V)	52.09	52.25	52.47	52.66	52.85
Short circuit current - $I_{sc}(A)$	15.16	15.24	15.31	15.39	15.47
MPP voltage - $V_{mp}(V)$	44.61	44.74	44.85	44.97	45.08
MPP current - I <sub>mp</sub> (A)	14.54	14.61	14.70	14.79	14.88
Irradiance ratio (rear/front)			13.5 %		

#### STRUCTURAL CHARACTERISTICS

3 ROCTORAL CHARACTERISTICS					
Module dimension (L*W*H)	89.69 x 44.65 x 1.18 inch (2278 x 1134 x 30 mm)				
Weight	59.97 lbs (27.2 kg)				
Number of cells	144 cells				
Cell	N-type monocrystalline (M10)				
Glass	Tempered, 3.2 mm AR, High transmittance, Low iron				
Backsheet	Transparent white mesh backsheet				
Frame	Anodized aluminum alloy				
Junction box	IP68 rated (3 diodes)				
Output wire	4mm² (IEC),12 AWG (UL)				
Wire length (Including Connector)	+400/-200mm (+15.75/-7.87in.)or customized				
Connector	MC4 Compatible				
Pieces per Pallet	36 pcs/Pallet				
Pieces per Container (Normal/Weight-limited area)	720/648 pcs/40°HQ				

## **OPERATING PARAMETERS**

Power tolerance (W)	(0,+5)
Maximum system voltage (V)	1500
Maximum rated fuse current (A)	30
Current operating temperature (°C)	-40~+185 °F (-40~+85 °C )
Bifaciality	80±10 %
Fire performance	Type 1


## **MECHANICAL LOADING**


Front side maximum static loading (Pa)	5400
Rear side maximum static loading (Pa)	2400
Hailstone test (mm)	35


## **TEMPERATURE RATINGS**


Temperature coefficient (P <sub>max</sub> )	-0.29 %/K
Temperature coefficient (V <sub>oc</sub> )	-0.28 %/K
Temperature coefficient (I <sub>sc</sub> )	+0.04 %/K
Nominal Module Operating Temperature	109.4±35.6 °F (43±2 °C)

## **MODULE DIMENSIONS (MM)**











Scan the QR code to get more information

Web: www.thornova-solar.com

E-mail: info@thornova-solar.com

\* The parameters delineated within this datasheet, both technical and monetary, may exhibit variations contingent upon the region. Thornova Solar provides no warranty as to their absolute accuracy. Owing to our unceasing commitment to innovation, research, development, and product enhancement. Thornova Solar provides no warranty as to their dasolute accuracy. Owing to our unceasing commitment to innovation, research, development, and product enhancement. Thornova Solar retains the discretion to amend any information encapsulation encapsulation of this datasheet without comporate it as an intrinsic component of the legally binding agreement ratified by both parties. The English renation of this datasheet serves purely as a point of reference. Should discrepancies arise between the English text and versions rendered in other languages, the stipulations of the English versions shall take procedure.



